




Linear Screen Cloths							
Weaving Type	Model	Thread Diameter (mm)		Density(No.s/cm)		Srength (N/cm)	Air Permeability (m³/m²h)
		Warp	Weft	Warp	Weft		
2-shed plain weaving fabric	05802	0.75	0.8	4.7-5	4.8-5	940	>20000
	05102	1.0	1.0	4.7-5.2	4.3-5	1600	>15000
	06702	0.7	0.7	8	7	≥1600	11000
	07102	0.7	1.0	6.6-7	4.3-4.6	1100	>15000
	08552	0.55	0.55	7.5-8	8.5-9	850	850-6500
	09452	0.45	0.45	10	8.6	1600	16000
	09502	0.5	0.5	8.5-9	10-10.5	750	>10000
	12502	0.5	0.5	13.5	8.5	1800	6500
3-shed plain weaving fabric	08603	0.5	0.6	10	9	1600	14000
	08903	0.9	0.9	7.8-8	5-5.5	2100	7500-8500
	07803	0.7	0.8	8	8	1600	10000
	20353	0.3	0.35	22	14.5	1200	13000
	20403	0.3	0.4	22	14.5	1200	13500




06702




07903




08602



09502



Edges Sealed by Glue



Edges Sealed by Heat Resistant Fabric